

Carles Drill Results

Hole	From	To	Thickness (metres)	True Thickness (metres)	Au, g/t	Ag, g/t	Cu, %	Core Recovery (%)
09CN10010R	124.5	136.4	11.9	8.0	4.2	13.7	0.72	96
including	124.5	127.9	3.5	2.3	5.7	31.4	1.85	93
09CN1011	161.2	170.4	9.2	4.6	3.9	11.8	0.48	97
including	163.4	164.5	1.2	0.6	6.8	35.7	1.34	97
including	168.2	170.4	2.2	1.1	6.0	8.2	0.30	98
09CN1012	142.8	154.6	11.8	5.5	11.0	61.1	0.80	96
including	142.8	145.7	2.8	1.3	16.1	193.5	1.98	93
including	147.5	149.9	2.3	1.1	31.1	62.6	1.23	100
09CN1013	179.4	180.8	1.5	0.6	2.6	1.7	0.12	97
	188.3	189.8	1.4	0.6	3.9	0.6	0.00	97
09CN1014	136.8	142.2	5.5	3.6	2.1	12.3	0.93	97
including	136.8	138.9	2.2	1.4	1.5	17.3	1.92	98
09CN1015	159.3	164.5	5.2	2.7	5.5	23.2	0.95	96
including	159.3	160.8	1.5	0.8	9.4	38.6	1.54	100
09CN1016	156.9	160.2	3.3	1.6	5.0	5.5	0.12	97
09CN1017R	187.3	189.2	1.9	0.6	1.8	7.4	0.29	100
09CN1018	158.2	172.1	13.9	6.1	2.4	12.6	0.98	100
including	170.3	172.1	1.8	0.8	6.7	37.2	1.41	100
09CN1019	170.5	176.1	5.6	3.7	6.2	1.1	0.08	100

True thicknesses were determined graphically by measuring the distance approximately perpendicular to vein contacts.