

A107 Drill Results

| Hole | From | To | True Thickness | | Au, g/t | Ag, g/t | Cu, % | Core Recovery (%) | |
|---------|-----------------|-------|----------------|----------|---------|---------|-------|-------------------|------|
| | | | (metres) | (metres) | | | | | |
| 09V1178 | 197.5 | 199.1 | 3.3 | 3.2 | 12.0 | 0.9 | 0.08 | 82 | Vein |
| | 208.2 | 209.7 | 1.5 | 1.5 | 4.6 | 2.2 | 0.09 | 40 | |
| 09V1179 | 140.4 | 142.2 | 1.9 | 1.5 | 11.6 | 60.3 | 3.30 | 46 | Vein |
| 09V1180 | 235.9 | 237.5 | 1.6 | 1.3 | 7.8 | 0.2 | 0.01 | 69 | Vein |
| 09V1181 | 194.4 | 211.2 | 16.8 | 11.1 | 3.8 | 1.1 | 0.04 | 69 | Vein |
| | 202.5 | 204.0 | 1.5 | 1.0 | 11.3 | 0.6 | 0.03 | 73 | |
| | 209.8 | 211.2 | 1.4 | 0.9 | 16.5 | 0.2 | 0.01 | 100 | |
| 09V1183 | 133.0 | 148.7 | 15.7 | 12.4 | 10.6 | 1.7 | 0.20 | 87 | Vein |
| | including 133.0 | 141.0 | 8.0 | 6.3 | 18.4 | 1.5 | 0.18 | 77 | |
| 09V1185 | 180.0 | 196.3 | 16.3 | 11.2 | 3.7 | 11.1 | 0.71 | 59 | Vein |
| | including 183.8 | 187.4 | 1.7 | 1.2 | 12.0 | 25.5 | 0.35 | 62 | |
| 09V1187 | 224.4 | 225.2 | 0.8 | 0.6 | 2.9 | 0.4 | 0.06 | 40 | Vein |
| | 229.3 | 230.4 | 1.2 | 0.9 | 3.7 | 0.2 | 0.02 | 100 | |
| 09V1189 | 264.8 | 270.1 | 5.4 | 2.1 | 3.3 | 21.4 | 0.52 | 98 | Vein |
| | including 267.8 | 270.1 | 2.4 | 0.9 | 5.6 | 47.6 | 1.17 | 100 | |
| 10V1192 | 151.2 | 155.8 | 4.6 | 3.1 | 20.5 | 1.1 | 0.25 | 100 | Vein |
| | including 151.2 | 153.1 | 1.9 | 1.3 | 46.4 | 0.6 | 0.03 | 100 | |
| | 169.2 | 173.3 | 4.1 | 2.8 | 3.4 | 0.3 | 0.03 | 95 | |

True thicknesses were determined graphically by measuring approximately perpendicular to the vein contacts.

San Martin Drill Results

| Hole | From | To | True Thickness | | Au, g/t | Ag, g/t | Cu, % | Core Recovery (%) | |
|---------|-----------------|-------|----------------|----------|---------|---------|-------|-------------------|----------------|
| | | | (metres) | (metres) | | | | | |
| 09V1182 | 153.2 | 154.7 | 1.5 | 0.7 | 10.3 | 38.3 | 2.52 | 100 | Vein (S107) |
| | 161.8 | 164.1 | 2.3 | 1.1 | 6.9 | 40.7 | 6.69 | 96 | |
| | 169.3 | 172.5 | 3.1 | 1.4 | 1.6 | 22.3 | 3.59 | 100 | |
| 09V1184 | 184.7 | 191.9 | 8.7 | 5.0 | 4.3 | 29.7 | 1.69 | 66 | Vein (S107) |
| | including 186.7 | 189.1 | 2.4 | 1.4 | 10.2 | 42.5 | 1.56 | 79 | |
| 09V1186 | 20.5 | 24.0 | 3.5 | 1.9 | 8.3 | 8.0 | 0.15 | 100 | Vein (S107) |
| | including 20.5 | 22.3 | 1.8 | 0.9 | 15.6 | 14.5 | 0.26 | 100 | |
| | 186.1 | 187.5 | 1.4 | 0.7 | 2.4 | 30.5 | 1.33 | 75 | |
| | 197.7 | 201.6 | 3.9 | 2.1 | 14.5 | 142.9 | 3.05 | 88 | |
| 09V1188 | 92.0 | 95.6 | 3.6 | 1.4 | 9.4 | 53.8 | 2.39 | 97 | Skarn |
| | including 94.5 | 95.6 | 1.1 | 0.4 | 21.5 | 85.8 | 5.91 | 95 | |
| 10V1193 | 259.5 | 262.1 | 2.6 | 1.7 | 14.2 | 5.1 | 0.49 | 100 | Vein (S107) |
| | 268.4 | 271.9 | 3.5 | 2.2 | 2.0 | 17.9 | 3.13 | 100 | |
| | including 271.0 | 271.9 | 0.9 | 0.6 | 5.8 | 51.2 | 9.45 | 100 | |

True thicknesses were determined graphically by measuring approximately perpendicular to the vein or skarn contacts.

Black Skarn (West)

| Hole | From | To | True Thickness | | Au, g/t | Ag, g/t | Cu, % | Core Recovery (%) | |
|---------|------|-------|----------------|----------|---------|---------|-------|-------------------|------------|
| | | | (metres) | (metres) | | | | | |
| 09V1190 | 99.7 | 109.3 | 9.6 | 9.4 | 12.5 | 7.1 | 0.38 | 54 | Skarn&Vein |
| 09V1191 | 58.0 | 59.0 | 1.1 | 1.0 | 2.8 | 1.6 | 0.13 | 76 | Skarn |

True thicknesses were determined graphically by measuring approximately perpendicular to the vein or skarn contacts.